



اتش ديليو

للعدسات الملصقه

## RGP Material Properties

Property	F2 Mid	F2 High	Optimum Comfort
Classification	Focon III 3	Focon III 4	Focon III 4
Light Transmission	>96%	>96%	>96%
Oxygen Permeability [DK] (Gas to Gas) @ 35° (barrers)	50	100	-
Oxygen permeability [DK] (ISO) @ 35°C (barrers)	33	42	65
Refractive Index	1.45	1.44	1.437
Shore D hardness	82	81	79
Wetting angle (captive bubble method)	19	21	Immeasurable
Handling tints	Green	Violet	Grey / Blue

\* The material are manufactured by CONTAMAC CO. LTD UK

\*\* Data in the table are given by CONTAMAC CO. LTD UK